

Ezi-Gun & Go® – Fitter!

Technical Product Data

Chemical base	1-C polyurethane								
Color	Black								
Cure mechanism	Moisture-curing								
Density (uncured)	1.2 kg/l approx.								
Non-sag properties	Very good								
Application temperature	5 - 35°C								
Tack-free time ¹	20 min approx.								
Open time ¹	15 min approx.								
Curing speed ¹	3 mm / 24 h approx.								
Shore A hardness (ISO 868)	65 approx.								
Tensile strength (ISO 37)	9 N/mm² approx.								
Elongation at break (ISO 37)	325% approx.								
Tear propagation resistance (ISO 34)	12 N/mm approx.								
Tensile lap-shear strength (ISO 4587)	5.5 N/mm² approx.								
Drive-Away Time ^{a/b} (cars) according to FMVSS 212 / 208	<table style="border: none; width: 100%;"> <tr> <td style="width: 50%;"></td> <td style="width: 50%; text-align: center;">twin airbags</td> </tr> <tr> <td></td> <td style="text-align: center;">without airbags</td> </tr> <tr> <td></td> <td style="text-align: center;">60 minutes</td> </tr> <tr> <td></td> <td style="text-align: center;">30 minutes</td> </tr> </table>		twin airbags		without airbags		60 minutes		30 minutes
	twin airbags								
	without airbags								
	60 minutes								
	30 minutes								
Volume resistivity (ASTM D 257-99)	10⁹ Ωcm approx.								
Shelf life (storage below 25°C)	9 months								

^{a)} 23°C (73°F) / 50% r.h.

^{b)} with seatbelt

Description

Ezi-Gun & Go® – Fitter! is a fast-curing, cold-applied windshield adhesive with high shear modulus. Easy to apply, with excellent technical characteristics (black-primerless, compatible with glass-mounted aerals, non-conductive).

Ezi-Gun & Go® – Fitter! is manufactured in accordance with ISO 9001 / 14001 quality assurance system and the responsible care program.

Product Benefits

- One-part polyurethane
- Short drive-away times to US safety standards FMVSS 212/208 (based on testing carried out with seatbelts, twin airbags fitted)
- Easy to apply, no pre-heating required
- short cut-off string
- very good non-sag characteristics
- Prevents contact corrosion in the case of aluminum bodies vehicles

Areas of Application

Ezi-Gun & Go® – Fitter! is to be used by professional experienced fitters only. If this product is used for other applications than Automotive Glass Replacement, tests with current substrates and conditions have to be performed by user to ensure adhesion and material compatibility.

Cure Mechanism

Ezi-Gun & Go® – Fitter! cures by reaction with atmospheric moisture.

Chemical Resistance

Ezi-Gun & Go® – Fitter! is resistant to water and proprietary aqueous cleaning agents (including windscreen cleaners containing alcohol); temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, alcohol, concentrated mineral acids and caustic solutions or paint thinners.

Method of Application

Removal of old windows

Remove damaged glass in accordance with the vehicle manufacturer's instructions.

Surface preparation

Surfaces must be clean, dry and free from all traces of dust and grease. The bond faces must be treated with a cleaning and activating agent or primed with the appropriate primer.

Application

Cut off the tip of the nozzle in accordance with the vehicle manufacturer's recommendation and screw onto the sausage adapter.

It is recommended to apply the adhesive with a piston-type application gun. To ensure a uniform thickness of the adhesive bead, we recommend that the adhesive be applied in the form of a triangular bead.

The substrate temperature must be between 5°C and 40°C.

Removal

Uncured Ezi-Gun & Go® – Fitter! may be removed from tools and equipment with Direct Glazing Adhesive Remover or another suitable solvent. Once cured, the material can only be removed mechanically.

Do not use solvents to clean hands or exposed skin.

Further Information

Available at www.laddaw.co.uk and copies of the following publications are available on request:

- Material Safety Data Sheet

Packaging Information

Unipack – 400ml

Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

Legal Notes

Laddaw and its affiliates do not represent or make any warranty in respect of the accuracy or reliability of the information. The information, and, in particular, the recommendations relating to the application and end-use of Laddaw products, are given in good faith based on Laddaw's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Laddaw's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of satisfactory quality, merchantability or of fitness for a particular purpose in respect to any Laddaw products, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered and Laddaw hereby expressly disclaims any and all such warranties and liability, express or implied, to the extent permitted by applicable law. Any reliance placed upon the information herein or the recommendations is solely the responsibility of the user of the product. The user of the product must test the product's suitability for the intended application and purpose to satisfy itself that it meets the user's requirements. Laddaw reserves the right to change the properties of its products and thereby any product specifications are subject to change and may vary from those shown without notice. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.